

ECORE International
715 Fountain Ave
Lancaster, PA 17601

Product Data 34-G

Product Class: Composition Cork

<u>Property</u>	<u>Test Method</u>	<u>Result</u>	<u>Unit</u>
Density	ASTM D3676	30 min	PCF
Density	ASTM D3676	481 min	Kg/m3
Tensile Strength	ASTM F152	300 min	PSI
Compression 100 psi	ASTM F36	5 - 15	Recovery 75 Percent
Shore A Hardness	ASTM D2240	65 - 85	Points

This material has a shelf life of 2 years from date of manufacture when protected from environmental extremes.

The values shown represent current production and may vary under different conditions.

-