

ECORE International
715 Fountain Ave.
Lancaster, PA 17601

DR-106

Product Class: Composition Cork

Product Data DR-106
(Available in sheets as N-106)

| <u>Property</u> | <u>Test Method</u> | <u>Result</u> | <u>Unit</u> |
|------------------------|--|---------------|-------------------------------|
| Density | ASTM D3676 | 17.0 min | PCF |
| Density | ASTM D3676 | 272 min | Kg/m3 |
| Tensile Strength | ASTM F152 | 100 min | PSI |
| Compression 100 psi | ASTM F36 | 20-40 | Recovery 75 min Percent |
| Flexibility | ASTM F147 | 5 Max | Factor |
| Meets Specification: | ASTM F104 MIL-G-12803 P2127B F216000RT Fed. HH-C-576, Class 2, Type II | | |

This material has a shelf life of 2 years from date of manufacture when protected from environmental extremes.

The values shown represent current production and may vary under different conditions.

