

ECORE International
715 Fountain Ave.
Lancaster, PA 17601

MA-40

Product Class: Composition Cork

Product Data MA-40
(Available in sheets as N-101)

<u>Property</u>	<u>Test Method</u>	<u>Result</u>	<u>Unit</u>
Density	ASTM D3676	27.5 min	PCF
Density	ASTM D3676	440 min	Kg/m3
Tensile Strength	ASTM F152	300 min	PSI
Compression 100 psi	ASTM F36	5-15	Recovery 75 min Percent
Binder	ASTM D2000	Resin / Polymeric	
Flexibility	ASTM F147	5 Max	Factor

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

The values shown represent current production and may vary under different conditions.

