

ECORE International
715 Fountain Ave.
Lancaster, PA 17601

711-BNF

Product Class: Cork/Rubber

Product Data 711-BNF

Property	Test Method	Result	Unit
Density	ASTM D3676	60.0 min	PCF
Density	ASTM D3676	880 min	Kg/m3
Tensile Strength	ASTM D412	300 min	PSI
Compression 400 psi	ASTM F36	15-25	Recovery 75 min Percent
Shore A Hardness	ASTM D2240	70-85	Points
Flexibility	ASTM F147	3 max	Factor
Coefficient of Friction Dry		0.6	
Wet		0.14	
Compression Set B 25% deflection, 22 hrs. at 158°F	ASTM D395	55 max	Percent

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

The values shown represent current production and may vary under different conditions.

