

ECORE International
715 Fountain Ave.
Lancaster, PA 17601

GRC-37

Product Class: Cork/Rubber

Product Data GRC-37

<u>Property</u>	<u>Test Method</u>	<u>Result</u>	<u>Unit</u>
Binder	ASTM D2000	Co-Polymer	
Density	ASTM D3676	45.0 min	PCF
Density	ASTM D3676	720 min	Kg/m ³
Tensile Strength	ASTM F152	200 min	PSI
Compression 400 psi	ASTM F36	35-45	Recovery 80 min Percent
Shore A Hardness	ASTM D2240	60-80	Points
Flexibility	ASTM F147	1 max	Factor
Fluid Immersion 70 hrs. at 212°F	ASTM F146	Volume	
Oil 1		-5 to +15	Percent
Oil 3		0 to +30	Percent
Fuel A (22 hrs. at Room Temp.)		0 to +15	Percent

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

The values shown represent current production and may vary under different conditions.

