

ECORE International  
 715 Fountain Ave.  
 Lancaster, PA 17601

# 7619

**Product Class: Rubber**

**Product Data 7619**

<u>Property</u>	<u>Test Method</u>	<u>Result</u>	<u>Unit</u>	
Density	ASTM D297	0.75 min	g/cm <sup>3</sup>	
Tensile Strength	ASTM D412, Die C	100 min	PSI	
Elongation	ASTM D412, Die C	65 min	Percent	
Compression	ASTM F36	Compression	Recovery	
50 psi		10-20	80 min	Percent
100 psi		25-35	85 min	Percent
200 psi		40-50	90 min	Percent
Shore A Hardness	ASTM D2240	50 ± 5	Points	
Tear Strength	ASTM D624, Die C	30 min	PPI	
Flexibility	ASTM F147	0-1	Factor	
Compression Set B 25% deflection, 22 hrs. at 158°F	ASTM D395	26	Percent	
Compression Set (Foam) 50% deflection, 22 hrs. at 158°F	ASTM D3676	19	Percent	

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

***The values shown represent current production and may vary under different conditions.***

