



ECORE International
715 Fountain Ave
Lancaster, PA 17601
phone: 717-295-3400

Product Data 7619 III

Product Class: All Rubber

<u>Property</u>	<u>Test Method</u>	<u>Typical Results</u>
Density	ASTM D297	56 lbs/ft ³ , minimum
Tensile Strength	ASTM D412, Die C	200 psi, min.
Elongation	ASTM D412, Die C	100%, min.
Tear Strength	ASTM D624, Die C	80 ppi, min.
Shore A Hardness	ASTM D2240	60 ± 5
Coefficient of Friction	ASTM D1894	1.2
Flexibility	ASTM F147	0 factor, maximum
Heat Aging 70 hours @ 158°F	ASTM D573	
Change in Tensile		-7%
Change in Elongation		-11%
Change in Hardness (Shore A)		+2

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

The values shown represent current production and may vary under different conditions.