

ECORE International  
715 Fountain Ave.  
Lancaster, PA 17601

# RA-65

**Product Class: Rubber**

**Product Data RA-65**  
For general fluid sealing applications

<b>Property</b>	<b>Test Method</b>	<b>Result</b>	<b>Unit</b>
Density	ASTM D297	66 min	PCF
Tensile Strength	ASTM D412, Die C	500 min	PSI
Elongation	ASTM D412, Die C	80 min	Percent
Tear Strength	ASTM 624, Die C	150 min	PPI
Compression 400 psi	ASTM F36	15-25	Recovery 85 min Percent
Shore A Hardness	ASTM D2240	65-75	Points
Flexibility	ASTM F147	0	Factor

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

***The values shown represent current production and may vary under different conditions.***

