



N-101 & DR-101

Product Class: Composition Cork

<u>Property</u>	<u>Test Method</u>	<u>Typical Result</u>
Density	ASTM D3676	15.8 lbs./ft ³ (0.25 g/cm ³)
Tensile Strength	ASTM F152	125 lbs./in ² (862 kPa)
Compression @ 100 psi	ASTM F36	36%
Recovery		83%
Flexibility	ASTM F147	5 max.
Meets the following specs:	ASTM F104 F217000RT MIL-G-12803 P2128A HH-C-576b, Class 1, Type II	

This material has a shelf life of 2 years from date of manufacture when protected from environmental extremes.

The values shown represent current production and may vary under different conditions.

PS 187 N-101 & DR-101 (8035 & 8021)
REV 101015
WMW