

**Product Class: Cork / Rubber**

<u>Property</u>	<u>Test Method</u>	<u>Typical Result</u>
Density	ASTM D3676	40.1 lbs./ft <sup>3</sup> (0.64 g/cm <sup>3</sup> )
Tensile Strength	ASTM F152	295 lbs./in <sup>2</sup> (2030 kPa)
Compression @ 200 psi	ASTM F36	25% (Recovery 95%)
@ 400 psi		39% (Recovery 81%)
Flexibility	ASTM F147	3 max.
Shore A Hardness	ASTM D2240	60 to 75
Compression Set B	ASTM D395	80% max.
25% deflection, 22 hrs. @ 158°F		
Fluid Immersion	ASTM F146	change in volume
Oil 1	70 hrs. @ 212°F	-5 to +10%
Oil 3	70 hrs. @ 212°F	-2 to +15%
Fuel A	22 hrs. @ 75°F	-2 to +10%
Temperature Range	- 40° to + 250°F (-40° to + 121°C)	
Meets the following specs:	ASTM F104 F227000 M2 T MIL-G-12803 P2256A AMS-C-6183 (MIL-C-6183b) Type I or II, Cl 1, Gr A	

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

*The values shown represent current production and may vary under different conditions.*