

Product Class: Cork / Rubber

<u>Property</u>	<u>Test Method</u>	<u>Typical Result</u>
Density	ASTM D3676	40.1 lbs./ft ³ (0.64 g/cm ³)
Tensile Strength	ASTM F152	295 lbs./in ² (2.0 MPa)
Compression @ 200 psi	ASTM F36	25% (Recovery 95%)
@ 400 psi		40% (Recovery 80%)
Flexibility	ASTM F147	3 max.
Shore A Hardness	ASTM D2240	65
Compression Set B	ASTM D395	80% max.
25% deflection, 22 hrs. @ 158°F		
Fluid Immersion	ASTM F146	change in volume
Oil 1	70 hrs. @ 212°F	-2 to +10%
Oil 3	70 hrs. @ 212°F	0 to +15%
Fuel A	22 hrs. @ 75°F	0 to +10%
Temperature Range	- 40° to + 250°F (-40° to + 121°C)	
Meets the following specs:	ASTM F104 F227000 M2 T MIL-G-12803 P2256A AMS-C-6183 (previously MIL-C-6183b) Type I or II, Cl 1, Gr A	
This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.		

The values shown represent current production and may vary under different conditions.

Document #: CRP01.RD.PSL.PS.0043
Revision #: 2
Revision (Date): 8/1/2022
Expiration Date: 8/1/2025
Approved By: W.Welch

Doc Name: Public Spec H35 (8030)

Revision	Date	Revised by	Changes
New	6/21/2016	W.Welch	Creation of the Public Spec.
1	6/7/2019	W.Welch	Three year review; no change.
2	8/1/2022	W.Welch	Added part number; updated Immersion data.