

Product Class: Rubber

| <u>Property</u> | <u>Test Method</u> | <u>Typical Result</u> |
|-----------------------|--------------------|--|
| Density | ASTM D297 | 68 lbs./ft ³ (1.1 g/cm ³) |
| Tensile Strength | ASTM D412, Die C | 900 lbs./in ² (6.2 MPa) |
| Elongation | ASTM D412, Die C | 170% |
| Tear Strength | ASTM D624, Die C | 230 lbs./in. (40 N/mm) |
| Shore A Hardness | ASTM D2240 | 72 |
| Flexibility | ASTM F147 | 1 |
| Compression @ 400 psi | ASTM F36 | 20% |
| Recovery | | 88% |

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

The values shown represent current production and may vary under different conditions.

Document #: CRP01.RD.PSL.PS.0050
 Revision #: 2
 Revision (Date): 8/1/2022
 Expiration Date: 8/1/2025
 Approved By: W.Welch

Doc Name: Public Spec RA-65 (8015)

| Revision | Date | Revised by | Changes |
|----------|-----------|------------|---|
| New | 6/21/2016 | W.Welch | Creation of the Public Spec. |
| 1 | 6/7/2019 | W.Welch | Three year review; no change. |
| 2 | 8/1/2022 | W.Welch | Added part number; updated data & metric. |
| | | | |