

Product Class: Rubber

<u>Property</u>	<u>Test Method</u>	<u>Typical Result</u>
Density	ASTM D297	67.5 lbs./ft ³ (1.08 g/cm ³)
Tensile Strength	ASTM D412-Die C	
parallel to grain flow		825 lbs./in ² (5.7 MPa)
perpendicular to grain flow		1000 lbs./in ² (6.9 MPa)
Elongation	ASTM D412-Die C	
parallel to grain flow		160%
perpendicular to grain flow		170%
Tear Strength	ASTM D624 - Die C	
parallel to grain flow		275 lbs./inch (48.1 N/mm)
perpendicular to grain flow		325 lbs./inch (56.9 N/mm)
Durometer Hardness, Shore A	ASTM D2240	75
Temperature Range		-40 to 250°F (-40 to 121°C)
Heat Aging	ASTM D573-Die C	
Change in Tensile		± 25 max
Change in Elongation		± 25 max
Change in Hardness (Shore A)		± 10 max
This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.		

The values shown represent current production and may vary under different conditions.

Document #: CRP01.RD.PSL.PS.0007
Revision #: 2
Revision (Date): 8/1/2022
Expiration Date: 8/1/2025
Approved By: W.Welch

Doc Name:	Public Spec 8620 (8007)				
-----------	-------------------------	--	--	--	--

Revision	Date	Revised by	Changes
New	6/21/2016	W.Welch	Creation of the Public Spec.
1	6/7/2019	W.Welch	Density was added above the Tensile
2	8/1/2022	W.Welch	Added part number.