Product Class: Cork / Rubber

<u>Property</u>	Test Method	Typical Result
Density	ASTM D3676	35.7 lbs./ft ³ (0.57 g/cm ³)
Tensile Strength	ASTM F152	240 lbs./in ² (1660 kPa)
Compression @ 400 psi Recovery	ASTM F36	45% 80%
recovery		0070
Flexibility	ASTM F147	3 max.
Shore A Hardness	ASTM D2240	63
Compression Set B 25% deflection, 22 hrs		55% max
Fluid Immersion Oil 1	ASTM F146 70 hrs. @ 212°F	change in volume -5 to +15%
Oil 3	70 hrs. @ 212°F	+5 to +50%
Fuel A	22 hrs. @ 75°F	0 to +35%
Temperature Range	- 40° to + 250°F (-40° to + 121°C)	

The values shown represent current production and may vary under different conditions.

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

Meets the following specs: ASTM F104 F227000 M1 T MIL-G-12803 P2255B

PS-241 GRC-35 E20 REV 103015 WMW